

Advanced quantum many-body methods for magnetic molecules: what theory can do for you


Jürgen Schnack

Department of Physics – University of Bielefeld – Germany

<http://obelix.physik.uni-bielefeld.de/~schnack/>


Seminar, Prof. Oshio's group

18. 06. 2015, Tsukuba, Japan




The problem

You have got a molecule!



Congratulations!

You want to build a quantum computer!




Very smart!


You have got an idea about the modeling!

$$\tilde{H} = -2 \sum_{i < j} J_{ij} \vec{s}(i) \cdot \vec{s}(j) + g \mu_B B \sum_i^N s_z(i)$$

Heisenberg
Zeeman




In the end it's always a big matrix!



$$\text{Fe}_{10}^{\text{III}}: N = 10, s = 5/2$$

Dimension=**60,466,176**. Maybe **too** big?

Thank God, we have computers



“Espresso-doped multi-core”

128 cores, 384 GB RAM

... but that's not enough!

Contents for you today



$$\begin{pmatrix} 3 & 42 & 4711 \\ 42 & 0 & 3.14 \\ 4711 & 3.14 & 8 \\ -17 & 007 & 13 \\ 1.8 & 15 & 081 \end{pmatrix}$$


1. Complete diagonalization
2. Odd-membered rings!
3. FTLM
4. Magnetocalorics
5. Deposited spins

We are the sledgehammer team of matrix diagonalization.
Please send inquiries to jschnack@uni-bielefeld.de!

Yes, we can!

(Treat spin systems with dimensions up to 10^{10} .)

Irreducible Tensor Operator approach



Spin rotational symmetry SU(2):

- $\underline{H} = -2 \sum_{i < j} J_{ij} \underline{\tilde{S}}_i \cdot \underline{\tilde{S}}_j + g\mu_B \underline{\tilde{S}} \cdot \underline{B}$;

- Physicists employ: $[\underline{H}, \underline{S}_z] = 0$;

- Chemists employ: $[\underline{H}, \underline{S}^2] = 0, [\underline{H}, \underline{S}_z] = 0$;


Irreducible Tensor Operator (ITO) approach;
Free program MAGPACK (2) available.

(1) D. Gatteschi and L. Pardi, *Gazz. Chim. Ital.* **123**, 231 (1993).

(2) J. J. Borrás-Almenar, J. M. Clemente-Juan, E. Coronado, and B. S. Tsukerblat, *Inorg. Chem.* **38**, 6081 (1999).

(3) B. S. Tsukerblat, *Group theory in chemistry and spectroscopy: a simple guide to advanced usage*, 2nd ed. (Dover Publications, Mineola, New York, 2006).

Point Group Symmetry






- Point groups, e.g. O_h or I_h , realized as permutations;
- Hamiltonian commutes with all group operations:

$$[\tilde{H}, \tilde{G}_i] = 0;$$
- Construct irreducible representations and related Hamilton matrices;
 No free program available (4).


(1) M. Tinkham, *Group Theory and Quantum Mechanics*, Dover.
 (2) D. Gatteschi and L. Pardi, *Gazz. Chim. Ital.* **123**, 231 (1993).
 (3) O. Waldmann, *Phys. Rev. B* **61**, 6138 (2000).
 (4) R. Schnalle and J. Schnack, *Int. Rev. Phys. Chem.* **29**, 403-452 (2010) ⇐ contains EVERYTHING.

Example: Fe₁₀ – SU(2) & D₂





Spin ring, $N = 10$, $s = 5/2$, Hilbert space dimension 60,466,176; symmetry D_2 (1).

- (1) R. Schnalle and J. Schnack, *Int. Rev. Phys. Chem.* **29**, 403-452 (2010).
- (2) C. Delfs *et al.*, *Inorg. Chem.* **32**, 3099 (1993).



Example: Icosahedron – SU(2) & I_h




Icosahedron, $s = 3/2$, Hilbert space dimension 16,777,216; symmetry I_h ;
 Evaluation of recoupling coefficients for $s = 3/2$ in I_h **practically impossible** (1).

(1) R. Schnalle and J. Schnack, Int. Rev. Phys. Chem. **29**, 403-452 (2010).

Frustration effects

Definition of frustration




- **Simple:** A spin system is frustrated if in the ground state of the corresponding classical spin system not all interactions can be minimized simultaneously.

- **Advanced:** A non-bipartite antiferromagnet is frustrated. A bipartite spin system can be decomposed into two sublattices A and B such that for all exchange couplings:

$$J(x_A, y_B) \leq g^2, J(x_A, y_A) \geq g^2, J(x_B, y_B) \geq g^2, \text{cmp. (1,2).}$$

- (1) E.H. Lieb, T.D. Schultz, and D.C. Mattis, Ann. Phys. (N.Y.) **16**, 407 (1961)
- (2) E.H. Lieb and D.C. Mattis, J. Math. Phys. **3**, 749 (1962)

Marshall-Peierls sign rule for even rings



- Expanding the ground state in $\mathcal{H}(M)$ in the product basis yields a sign rule for the coefficients

$$|\Psi_0\rangle = \sum_{\vec{m}} c(\vec{m}) |\vec{m}\rangle \quad \text{with} \quad \sum_{i=1}^N m_i = M$$

$$c(\vec{m}) = (-1)^{\left(\frac{N_s}{2} - \sum_{i=1}^{N/2} m_{2i}\right)} a(\vec{m})$$


All $a(\mathbf{m})$ are non-zero, real, and of equal sign.

- Yields eigenvalues for the shift operator \tilde{T} :

$$\exp\left\{-i\frac{2\pi k}{N}\right\} \quad \text{with} \quad k \equiv a\frac{N}{2} \pmod{N}, \quad a = N_s - M$$

(1) W. Marshall, Proc. Royal. Soc. A (London) **232**, 48 (1955)

Numerical findings for odd rings



- For odd N and half integer s , i.e. $s = 1/2, 3/2, 5/2, \dots$ we find that (1)
 - the ground state has total spin $S = 1/2$;
 - the ground state energy is **fourfold** degenerate.
- Reason: In addition to the (trivial) degeneracy due to $M = \pm 1/2$, a degeneracy with respect to k appears (2):

$$k = \lfloor \frac{N+1}{4} \rfloor \text{ and } k = N - \lfloor \frac{N+1}{4} \rfloor$$

- For the first excited state similar rules could be numerically established (3).

(1) K. Bärwinkel, H.-J. Schmidt, J. Schnack, J. Magn. Magn. Mater. **220**, 227 (2000)

(2) $\lfloor \cdot \rfloor$ largest integer, smaller or equal

(3) J. Schnack, Phys. Rev. B **62**, 14855 (2000)

k-rule for odd rings

- An extended k-rule can be inferred from our numerical investigations which yields the k quantum number for relative ground states of subspaces $\mathcal{H}(M)$ for even as well as odd spin rings, i.e. **for all rings** (1)

$$k \equiv \pm a \left\lceil \frac{N}{2} \right\rceil \pmod{N}, \quad a = Ns - M$$

k is independent of s for a given N and a . The degeneracy is minimal ($N \neq 3$).

N	s	a									
		0	1	2	3	4	5	6	7	8	9
8	1/2	0	4	$8 \equiv 0$	$12 \equiv 4$	$16 \equiv 0$	-	-	-	-	-
9	1/2	0	$5 \equiv 4$	$10 \equiv 1$	$15 \equiv 3$	$20 \equiv 2$	-	-	-	-	-
9	1	0	$5 \equiv 4$	$10 \equiv 1$	$15 \equiv 3$	$20 \equiv 2$	$25 \equiv 2$	$30 \equiv 3$	$35 \equiv 1$	$40 \equiv 4$	$45 \equiv 0$

No general, but partial proof yet.

(1) K. Bärwinkel, P. Hage, H.-J. Schmidt, and J. Schnack, Phys. Rev. B **68**, 054422 (2003)

What if your molecule is BIGGER?




K-Computer?

Finite-temperature Lanczos Method

(Good for dimensions up to 10^{10} .)

Lanczos – a Krylov space method



- Idea: exact diagonalization in reduced basis sets.
- But which set to choose???
- Idea: generate the basis set with the operator you want to diagonalize:
 $\{ |\phi\rangle, \tilde{H} |\phi\rangle, \tilde{H}^2 |\phi\rangle, \tilde{H}^3 |\phi\rangle, \dots \}$
- But which starting vector to choose???
- Idea: almost any will do!
- Cornelius Lanczos (Lánczos Kornél, 1893-1974)

(1) C. Lanczos, J. Res. Nat. Bur. Stand. **45**, 255 (1950).

Finite-temperature Lanczos Method I

$$Z(T, B) = \sum_{\nu} \langle \nu | \exp \left\{ -\beta \tilde{H} \right\} | \nu \rangle$$



$$\langle \nu | \exp \left\{ -\beta \tilde{H} \right\} | \nu \rangle \approx \sum_n \langle \nu | n(\nu) \rangle \exp \left\{ -\beta \epsilon_n \right\} \langle n(\nu) | \nu \rangle$$

$$Z(T, B) \approx \frac{\dim(\mathcal{H})}{R} \sum_{\nu=1}^R \sum_{n=1}^{N_L} \exp \left\{ -\beta \epsilon_n \right\} |\langle n(\nu) | \nu \rangle|^2$$

- $|n(\nu)\rangle$ n-th Lanczos eigenvector starting from $|\nu\rangle$
- Partition function replaced by a small sum: $R = 1 \dots 10, N_L \approx 100$.

J. Jaklic and P. Prelovsek, Phys. Rev. B **49**, 5065 (1994).


How good is finite-temperature Lanczos?



- Works very well: compare frustrated cuboctahedron.
- $N = 12, s = 3/2$: Considered $< 100,000$ states instead of 16,777,216.

Exact results: R. Schnalle and J. Schnack, *Int. Rev. Phys. Chem.* **29**, 403-452 (2010).
 FTLM: J. Schnack and O. Wendland, *Eur. Phys. J. B* **78**, 535-541 (2010).

Icosidodecahedron $s = 1/2$



Exp. data: A. M. Todea, A. Merca, H. Bögge, T. Glaser, L. Engelhardt, R. Prozorov, M. Luban, A. Müller, Chem. Commun., 3351 (2009).



Finite-temperature Lanczos Method III

$$\tilde{H} = -2 \sum_{i < j} \vec{\tilde{s}}_i \cdot \mathbf{J}_{ij} \cdot \vec{\tilde{s}}_j + \sum_i \vec{\tilde{s}}_i \cdot \mathbf{D}_i \cdot \vec{\tilde{s}}_i + \mu_B B \sum_i g_i \tilde{s}_i^z$$

- **Problem:** for anisotropic Hamiltonians no symmetry left
→ accuracy drops (esp. for high T).
- Simple traces such as $\text{Tr} \left(\tilde{S}^z \right) = 0$ tend to be wrong for R not very big.

O. Hanebaum, J. Schnack, Eur. Phys. J. B **87**, 194 (2014)

Glaser-type molecules: $\text{Mn}_6^{\text{III}}\text{Cr}^{\text{III}}$




$s = 2, s = 3/2$
 $\dim(\mathcal{H}) = 62,500$
 non-collinear easy axes

Hours compared to days, notebook compared to supercomputer!

O. Hanebaum, J. Schnack, Eur. Phys. J. B **87**, 194 (2014)

T. Glaser, Chem. Commun. **47**, 116-130 (2011)


Effective magnetic moment of Mn₁₂-acetate



We can check DFT parameter predictions for large molecules!

O. Hanebaum, J. Schnack, work in progress

Effective magnetic moment of Mn₁₂-acetate



We can check DFT parameter predictions for large molecules!

O. Hanebaum, J. Schnack, work in progress

The magnetocaloric effect


Magnetocaloric effect – Basics



- Heating or cooling in a varying magnetic field. Predicted, discussed, discovered by Thomson, Warburg, Weiss, and Piccard (1).
- Typical rates: 0.5 . . . 2 K/T.
- Giant magnetocaloric effect: 3 . . . 4 K/T e.g. in $\text{Gd}_5(\text{Si}_x\text{Ge}_{1-x})_4$ alloys ($x \leq 0.5$).
- **Scientific goal I: room temperature applications.**
- **Scientific goal II: sub-Kelvin cooling.**

(1) A. Smith, Eur. Phys. J. H **38**, 507 (2013).

Sub-Kelvin cooling: Nobel prize 1949



The Nobel Prize in Chemistry 1949 was awarded to William F. Giaouque *for his contributions in the field of chemical thermodynamics, particularly concerning the behaviour of substances at extremely low temperatures.*

Sub-Kelvin cooling: Nobel prize 1949

768

LETTERS TO THE EDITOR

Attainment of Temperatures Below 1° Absolute by Demagnetization of $\text{Gd}_2(\text{SO}_4)_3 \cdot 8\text{H}_2\text{O}$

We have recently carried out some preliminary experiments on the adiabatic demagnetization of $\text{Gd}_2(\text{SO}_4)_3 \cdot 8\text{H}_2\text{O}$ at the temperatures of liquid helium. As previously predicted by one of us, a large fractional lowering of the absolute temperature was obtained.

An iron-free solenoid producing a field of about 8000 gauss was used for all the measurements. The amount of $\text{Gd}_2(\text{SO}_4)_3 \cdot 8\text{H}_2\text{O}$ was 61 g. The observations were checked by many repetitions of the cooling. The temperatures were measured by means of the inductance of a coil surrounding the gadolinium sulfate. The coil was immersed in liquid helium and isolated from the gadolinium by means of an evacuated space. The thermometer was in excellent agreement with the temperature of liquid helium as indicated by its vapor pressure down to 1.5°K.

On March 19, starting at a temperature of about 3.4°K, the material cooled to 0.53°K. On April 8, starting at about 2°, a temperature of 0.34°K was reached. On April 9, starting at about 1.5°, a temperature of 0.25°K was attained.


It is apparent that it will be possible to obtain much lower temperatures, especially when successive demagnetizations are utilized.

W. F. GIAUQUE
D. P. MACDOUGALL

Department of Chemistry,
University of California,
Berkeley, California,
April 12, 1933.


W. F. Giauque and D. MacDougall, *Phys. Rev.* **43**, 768 (1933).

Magnetocaloric effect – Paramagnets




- Ideal paramagnet: $S(T, B) = f(B/T)$, i.e. $S = const \Rightarrow T \propto B$.
- At low T pronounced effects of dipolar interaction prevent further effective cooling.

Magnetocaloric effect – af $s = 1/2$ dimer



- Singlet-triplet level crossing causes a peak of S at $T \approx 0$ as function of B .
- $M(T = 0, B)$ and $S(T = 0, B)$ not analytic as function of B .
- $M(T = 0, B)$ jumps at B_c ; $S(T = 0, B_c) = k_B \ln 2$, otherwise zero.

Magnetocaloric effect – af $s = 1/2$ dimer



blue lines: ideal paramagnet, red curves: af dimer

Magnetocaloric effect:


- (a) reduced,
- (b) the same,
- (c) enhanced,
- (d) opposite

when compared to an ideal paramagnet.

Case (d) does not occur for a paramagnet.

Nice ideas,
but can one measure it?
With magnetic molecules?

Gd₇ – Basics




- Often magnetocaloric observables not directly measured, but inferred from Maxwell's relations.
- First real cooling experiment with a molecule.
- $$\underline{H} = -2 \sum_{i < j} J_{ij} \vec{\tilde{s}}_i \cdot \vec{\tilde{s}}_j + g \mu_B B \sum_i^N \tilde{s}_i^z$$



 $J_1 = -0.090(5) \text{ K}, J_2 = -0.080(5) \text{ K}$
 and $g = 2.02$.
- **Very good agreement down to the lowest temperatures.**

J. W. Sharples, D. Collison, E. J. L. McInnes, J. Schnack, E. Palacios, M. Evangelisti, Nat. Commun. **5**, 5321 (2014).


Gd₇ – experiment & theory



J. W. Sharples, D. Collison, E. J. L. McInnes, J. Schnack, E. Palacios, M. Evangelisti, Nat. Commun. **5**, 5321 (2014).



Gd₇ – Experimental cooling







J. W. Sharples, D. Collison, E. J. L. McInnes, J. Schnack, E. Palacios, M. Evangelisti, Nat. Commun. **5**, 5321 (2014).

Numerical Renormalization Group calculations


(Good for deposited molecules.)

You want to deposit a molecule



M. Bernien *et al.*, Phys. Rev. Lett. **102**, 047202 (2009); A. Ghirriet *et al.*, ACS Nano, **5**, 7090-7099 (2011); X. Chen *et al.*, Phys. Rev. Lett. **101**, 197208 (2008); M. Mannini *et al.*, Nature Materials **8**, 194 - 197 (2009).

Physical example (ICMM 2010)




Stack of deposited Cobalt phthalocyanine (CoPc) molecules;
 Co^{2+} with spin $s = 1/2$.

Under which circumstances is the picture of total screening correct?

X. Chen *et al.*, Phys. Rev. Lett. **101**, 197208 (2008).

NRG – minimal model (already an approximation!)




- $\tilde{H} = \tilde{H}_{\text{electrons}} + \tilde{H}_{\text{coupling}} + \tilde{H}_{\text{impurity}}$

$$\tilde{H}_{\text{electrons}} = \sum_{i \neq j, \sigma} t_{ij} d_{i\sigma}^\dagger d_{j\sigma} + g_e \mu_B B S_z$$

$$\tilde{H}_{\text{coupling}} = -2J_A \tilde{S} \cdot \tilde{s}_0 \quad , \quad \tilde{s}_0 - \text{spin density at contact}$$
- $\tilde{H}_{\text{impurity}} = \text{Hamiltonian of your molecule!}$
- **NRG \equiv construction of a small (!) effective model in order to evaluate properties of the deposited cluster, the impurity (3).**

(1) K. G. Wilson, Rev. Mod. Phys. **47**, 773 (1975)
 (2) M. Höck, J. Schnack, Phys. Rev. B **87**, 184408 (2013)
 (3) *Impurity* is a technical term in this context and not an insult to chemists.

NRG in a cartoon





Metallic surface is replaced by semi-infinite Hubbard chain;

Parameters of the chain: hopping matrix elements and on-site energies;

Stepwise enlargement of the chain ($t_1 > t_2 > t_3 \dots$);


Truncation of basis set when matrices grow too big.

Once more: deposited chain




X. Chen *et al.*, Phys. Rev. Lett. **101**, 197208 (2008).

Energy levels of limiting cases for deposited trimer




- energy levels of a trimer



- energy levels of a dimer


Magnetization curves different; could be seen in XMCD.
 NRG calculates observables also between limiting cases
 and can thus tell under which circumstances a limiting case applies.

Increasing coupling to the substrate




H.-T. Langwald and J. Schnack, submitted; arXiv:1312.0864.

Increasing coupling to the substrate




H.-T. Langwald and J. Schnack, submitted; arXiv:1312.0864.

Increasing coupling to the substrate




H.-T. Langwald and J. Schnack, submitted; arXiv:1312.0864.

Increasing coupling to the substrate




H.-T. Langwald and J. Schnack, submitted; arXiv:1312.0864.

Increasing coupling to the substrate




H.-T. Langwald and J. Schnack, submitted; arXiv:1312.0864.

Increasing coupling to the substrate




H.-T. Langwald and J. Schnack, submitted; arXiv:1312.0864.

Weak vs. strong coupling



- weak coupling limit:
unperturbed molecule (trimer)

- $|J_A| \lesssim 0.1W$




- strong coupling limit:
effective remainder (dimer)

- $|J_A| \gtrsim 0.5W$

Inbetween: no simple characterization + further sequential screening possible

Summary



- Exact diagonalization is great but limited.
- Finite-Temperature Lanczos is a good approximate method for Hilbert space dimensions smaller than 10^{10} . The accuracy is amazing!
- FTLM works for anisotropic spin systems.
- Magnetic molecules for storage, q-bits, MCE, and since they are nice.

Many thanks to my collaborators worldwide

- M. Czopnik, T. Glaser, O. Hanebaum, Chr. Heesing, M. Höck, N.B. Ivanov, F. Kaiser, H.-T. Langwald, S. Leiding, A. Müller, R. Schnalle, Chr. Schröder, J. Ummethum (Bielefeld)
- K. Bärwinkel, H.-J. Schmidt, M. Neumann (Osnabrück)
- M. Luban (Ames Lab, USA); P. Kögerler (Aachen, Jülich, Ames); D. Collison, R.E.P. Winpenny, E.J.L. McInnes, F. Tuna (Man U); L. Cronin, M. Murrie (Glasgow); E. Brechin (Edinburgh); H. Nojiri (Sendai, Japan); A. Postnikov (Metz); W. Wernsdorfer (Grenoble); M. Evangelisti (Zaragosa); E. Garlatti, S. Carretta, G. Amoretti, P. Santini (Parma); Gopalan Rajaraman (Mumbai)
- J. Richter, J. Schulenburg (Magdeburg); A. Honecker (Göttingen); U. Kortz (Bremen); A. Tennant, B. Lake (HMI Berlin); B. Büchner, V. Kataev, H.-H. Klauß (Dresden); P. Chaudhuri (Mühlheim); J. Wosnitza (Dresden-Rossendorf); J. van Slageren (Stuttgart); R. Klingeler (Heidelberg); O. Waldmann (Freiburg)

Thank you very much for your
attention.

The end.

Molecular Magnetism Web

www.molmag.de

Highlights. Tutorials. Who is who. Conferences.